



# M60075

### **HIGH DENSITY POLYETHYLENE**

## FOR INJECTION MOULDING GRADE

 $M60075\ is\ a\ High\ Density\ Polyethylene\ (HDPE)\ grade\ suitable\ for\ injection\ moulding\ applications\ where\ good\ mechanical\ properties\ are$ essential with gloss, dimensional stability, good ESCR, required for technical mouldings like moulded crates, luggage shells, helmets, defence applications, etc.

Typical Characteristics			
Property	Test Method	Unit	Typical Value**
Density (23°C)	ASTM D1505	g/cc	0.960
MFI (190°C/2.16 kg)	ASTM D1238	g/10 min	8.0
Tensile Strength at Yield	ASTM D638	MPa	25
Elongation at Break	ASTM D638	%	800
Flexural Yield Strength	ASTM D790	MPa	30
Flexural Modulus	ASTM D790	MPa	900
Hardness	ASTM D2240	Shore D	69
Vicat Softening Point	ASTM D1525	°C	128
Izod Impact Strength	ASTM D256	J/m	88

#### **Applications**

Crates, Luggage and Industrial containers.

#### **Regulatory Information**

• Meets the requirements stipulated in standard IS: 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141-1982. The grade and the additives incorporated in it also comply with the FDA: CFR Title 21,177.1520, Olefin polymers.

#### Storage Recommendations

Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV/direct sunlight.

<sup>\*</sup>Typical Characteristics and not to be taken as specifications \*\*Mechanical Properties are on Injection Moulded Specimen