



SR20NC

RANDOM COPOLYMER FOR BLOW MOULDING & EXTRUSION

Repol SR20NC is recommended for **Blow Moulding and Extrusion** process. It is an ideal material to use in making clear bottles, containers, ball pen refills, sheets, stationery items and thermoformed products. The grade contains clarifier.

Repol SR20NC complies with the systemic and intracutaneous tests with four different extractants as per USP XXIX and I.P 96. The grade also complies with undue toxicity test as per E.P and skin irritation test as per I.S.

Typical Characteristics			
Property	Test Method	Unit	Typical Value*
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	gm/10 min	1.9
Tensile Strength at Yield (50mm/min)	ASTM D638	MPa	30
Elongation at Yield (50mm/min)	ASTM D638	%	12
Flexural Modulus (1% secant)	ASTM D790A	MPa	900
Notched Izod Impact Strength (23°C)	ASTM D256	J/m	100
Heat Deflection Temperature (455 kPa)	ASTM D648	°C	95

* Typical values, not to be taken as specification. All the mechanical properties as per ASTM D638 Type I specimen injection moulded in accordance with ASTM D4101

Applications

High clarity bottles, containers, sheets

Regulatory Information

Meets the requirements stipulated in IS 10910 on 'Specification for Polypropylene and its Copolymers for safe use in contact with foodstuff, pharmaceuticals, and drinking water'. Additives incorporated in this grade conform to the positive list of constituents as prescribed in IS 10909. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers

Storage Recommendations

Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight